

## Analysis of gallium nitride-based optical microring resonator with doped polymer grafting material

Hazura Haroon, Muhammad Syafiq Ramli, Siti Khadijah Idris, Anis Suhaila Mohd Zain,  
Hanim Abdul Razak, Thanigai Anbalagan

Fakulti Kejuruteraan Elektronik dan Kejuruteraan Komputer, Centre for Telecommunications Research & Innovation (CeTRI), Universiti Teknikal Malaysia Melaka, Melaka, Malaysia

### Article Info

#### Article history:

Received May 2, 2021

Revised Aug 31, 2021

Accepted Sep 6, 2021

#### Keywords:

GaN

Microring resonator

PMMA

Semiconductor design

### ABSTRACT

In this paper, the Gallium nitride-based optical microring resonator (OMR) filter with polymer grafting material (PMMA) coating was designed and optimized to predict its potential as a wavelength filtering device. The optimization was focused on the design parameters such as polymer thickness, gap separation variation, and the bus and ring waveguide widths. The target is to achieve the best output in terms of insertion loss (IL) and Extinction Ratio for wavelength-division multiplexing (WDM) applications, specifically for the use of the C-Band network. Upon completion, it was found that the optimized design was a ring radius of 10  $\mu\text{m}$  and PMMA thickness of 0.055  $\mu\text{m}$ , with the bus waveguide width of 800 nm and the output bus waveguide of 800 nm giving the observed IL of 0.07 dB and 87.3% extinction rate.

This is an open access article under the [CC BY-SA](https://creativecommons.org/licenses/by-sa/4.0/) license.



### Corresponding Author:

Hazura Haroon

Fakulti Kejuruteraan Elektronik Dan Kejuruteraan Komputer

Centre for Telecommunications Research & Innovation (CeTRI)

Universiti Teknikal Malaysia Melaka, Hang Tuah Jaya

76100 Durian Tunggal, Melaka, Malaysia

Email: hazura@utem.edu.my

## 1. INTRODUCTION

The optical microring resonator (OMR) is one of the optical telecommunication components commonly applied as a wavelength filtering function [1], [2]. Gallium nitride (GaN) is a semiconductor material with a large bandgap and is the most widely used material in the semiconductor industry after silicon. In this paper, the design of a gallium nitride-based OMR filter doped with polymer grafting material (PMMA) is reported. The design employed the research studies on the GaN and Sapphire ( $\text{Al}_2\text{O}_3$ ) as the add-drop filter of an OMR through the concept of coupling between a straight bus waveguide and a ring waveguide. The waveguide is then doped with the poly(methyl) methacrylate PMMA on top of the design to enhance the device performance [3]-[5].

The material PMMA has been applied as a polymer grafting material in the design of an OMR by many researchers including in the study of synthesized and characterized  $\text{Sm}^{3+}$  doped polymer optical waveguide amplifiers [6]-[9], the study of the effect of neutron irradiation on the optical properties of PMMA/RhB used in optical fiber amplification and the study of the effect of rare earth elements on the structural and optical properties of PMMA for possible uses in polymer optical communications [10]-[12].

It is known that Gallium nitride excels better as compared to silicon dioxide ( $\text{SiO}_2$ ) due to its vast features of stunning warm properties, a moderately large bandgap, mechanical hardness, high-temperature

dependability, and fantastic communicating range lucidity. GaN also has a lower energy bandgap of 3.4 eV, as compared to SiO<sub>2</sub> of only 1.1 eV. It will potentially serve as the key material for the next generation network of high-frequency and high-power transistors which be able to work at high temperatures, including in the form of light-emitting diodes (LEDs) and laser diodes [13]-[20].

Therefore, this study aims to propose the design of a Gallium nitride-based OMR to evaluate its performance as a wavelength filtering device in terms of insertion loss (IL) and extinction rate. To fulfill the desired application criteria, a thorough study is needed to determine the influence of those parameters. This study provides a guideline for determining the microring geometry to satisfy the desired filtering requirements.

## 2. RESEARCH METHOD

Figure 1 shows the 3D structure of the proposed optical microring resonator, which consists of a ring waveguide tightly coupled to two straight bus waveguides. The ring radius is represented by  $R$  and the gap separation is the separation distance between the straight and ring waveguides. The fully etched waveguide structure is taken into account in this study. The output power can be measured using the through and drop ports. For such a design, when the input light wave reaches resonance, it is coupled into the ring waveguide and then transferred to the drop port. On the other hand, if the resonance condition is not met, the light wave is delivered to the through port [21]. Two platforms were studied in this study; one is the conventional Si/SiO<sub>2</sub> platform, while the other one is the GaN/Sapphire platform.

The OMR performance was evaluated using a 3D electromagnetic simulator of the COMSOL software [22], [23]. It requires the user to configure the particular design of the waveguide by setting its length, width, depth, and radius for the waveguides. Then, another block was added as another substrate, which requires detailed attention towards its positioning and orientation, through vector values. Figure 2 depicts the graphic user interface for the component configuration settings.




Figure 1. The 3D structure of the proposed optical microring resonator




Figure 2. Component configuration

The sine-modulated gaussian pulse was utilized for the wave excitation in the input plane, and the excitation will occur along the Y-axis through a complex solver on the mode of full-vector (ADI-Method). As the optical pulse excitation along the straight waveguide was ready to be coupled into the ring waveguide, the OptiMode solver would configure and analyze them. The simulated design was then executed through the OptiFDTD simulator [24].

### 3. RESULTS AND DISCUSSION

The analysis had been done with varying several design parameters to see the effect of the microring resonator performance with the PMMA being applied on top of the GaN/Sapphire ( $\text{Al}_2\text{O}_3$ ). These parameters include the gap separation between the straight bus and the ring, PMMA thickness, and waveguide width.

#### 3.1. Initial design parameters value

Table 1 shows the initial design parameter values for the microring resonator. The device was designed to be working at the C-band telecommunication wavelength or around  $1550 \mu\text{m}$ . Other important parameters taken into account are the width of the straight ( $w_{\text{ring}}$ ) and ring ( $w_{\text{ring}}$ ) waveguides. Figure 3 depicts the side view of the proposed designs, in which the initial waveguide separation is  $125 \mu\text{m}$ . The proposed design features are as shown in: a ring size of  $10 \mu\text{m}$ , ring waveguide width of  $800 \text{ nm}$ , straight waveguide width of  $400 \text{ nm}$ , and gap separation of  $125 \mu\text{m}$ .

Table 1. Design specifications

Parameter	Value	Description
f0	193.414 THz	Frequency
wl0	1550 ( $\mu\text{m}$ )	Input $\lambda$
GaN	2.279	GaN R.I
Sapphire	1.76	$\text{Al}_2\text{O}_3$ R.I
time_steps	$10e^5$	Time steps
time_size	$8.339102 e^{-17}$	Time size
r0	10 ( $\mu\text{m}$ )	Radius of ring
w_core	400 (nm)	Straight width
w_ring	800 (nm)	Ring width
dx	125 ( $\mu\text{m}$ )	Gap separation




Figure 3. Schematic cross-section of the rib waveguide structures of the microring design based on the; (a) conventional Si/SiO<sub>2</sub> platform, (b) GaN/Al<sub>2</sub>O<sub>3</sub> platform

Figure 4 portrays the initial modeling of the basic structure using the GaN/Sapphire as the core of the add-drop filter of the OMR. The simulation was carried out to observe whether the wave or optical pulses could be coupled from the straight waveguide onto the ring waveguide due to its resonance ability. It can be seen that, with the input frequency capped around  $1550 \text{ nm}$ , a clear comparison can be made due to the design's ability to transmit the data for its round trip losses and coupling coefficient within the same shape configuration of ring size ( $10 \mu\text{m}$ ), ring waveguide width ( $800 \text{ nm}$ ), straight waveguide width ( $400 \text{ nm}$ ), and gap separation ( $125 \mu\text{m}$ ). The light will be able to be coupled through the port to the ring and finally transmitted to the drop port.




Figure 4. Optical pulses plot of GaN/Al<sub>2</sub>O<sub>3</sub> optical microring resonator

**3.2. Effect of the different microring resonator platform**

Figure 5 depicts the power spectrum for two different design platforms. One employs the SiO<sub>2</sub>/Silicon (Si) platform while the other one uses GaN/Sapphire measured at the drop port. It was observed that the GaN/Sapphire design has a very low IL of 0.099728353 dB at both 1.539389 μm and 1.554220 μm wavelengths, while the Si/SiO<sub>2</sub> platform has a 0.192454 dB loss. The output is supposedly in the ON-Resonance state where the peak of the spectrum can be observed. However, by utilizing the SiO<sub>2</sub> design, the light was not coupled from the straight waveguide to the ring waveguide as compared to the utilization of the GaN platform. For the SiO<sub>2</sub>/Si design, the signal will bypass the ring and exit at the through port-channel, hence, no signal arrives at the drop port.




Figure 5. Power spectrum of the optical resonator based on SiO<sub>2</sub>/Si and GaN platforms

**3.3. Effect of the variation of PMMA thickness**

Figure 6 shows the effect of doped PMMA thickness on top of the GaN/Al<sub>2</sub>O<sub>3</sub>. It can be seen that the smallest IL of 0.0675 dB was obtained with the PMMA thickness of 0.055 μm. This is due to its ability to couple much higher power from the input port through the port. The IL increases as the thickness of PMMA was increased. At 0.05 μm, due to the lack of stability, a high IL was observed. The result suggests that the lossy nature of the polymer film determines the optimum IL of the design and should be taken into account when designing an efficient microring resonator. The results can be validated by [21], where it shows that the thick PMMA guiding layer will induce large attenuation of the design devices.

### 3.4. Effect of the variations of gap separation

Using the same initial design configuration of 10  $\mu\text{m}$  ring size and 0.055  $\mu\text{m}$  PMMA polymer thickness, varying the gap separation to 125  $\mu\text{m}$ , 155  $\mu\text{m}$  and 205  $\mu\text{m}$  will produce different IL performances. The gap separation was chosen based on the nearest consecutive peaks at ON resonance condition around 1550 nm wavelength. From Figure 7, it was shown that the best configuration it could offer is at the thickness of 205  $\mu\text{m}$  with an IL of 0.099728352 dB. The highest IL occurs at 55  $\mu\text{m}$  since its coupling ability will degrade at very small gap separation due to the high propagation loss as described in [4].

In terms of the Extinction Rate, the Extinction Ratio percentage is calculated and analyzed by the ratio of average three or two-point lowest peaks over the average of the highest peaks to the percentage calculation [25]. Increasing the gap between the bus and the ring waveguide has a limited effect in reducing the coupling efficiency, thus reducing the extinction rate (%) [26]. However, aligning the straight and ring waveguides too close will cause the coupling factor to be smaller than the scattering loss per round trip, hence high loss and low ER can be predicted. Therefore, there must be an optimized distance between both. From Figure 8, it can be seen that the ER value can be optimized when the gap separation was fixed to 255  $\mu\text{m}$  with an ER of 74.1 %. Therefore, in achieving high ER, the gap separation of 255  $\mu\text{m}$  is recommended.




Figure 6. Insertion loss for different PMMA thicknesses




Figure 7. Gap separation effect on the insertion loss of OMR




Figure 8. Gap separation effect on the extinction rate of OMR

### 3.5. Effect of dissimilar straight-ring wavelength width

The effect of the straight and ring waveguide sizes on the microring performance was also studied. From the power spectrum depicted in Figure 9, it is shown that the lowest IL is observed for the straight waveguide width of 600  $\mu\text{m}$  and the ring waveguide of 800  $\mu\text{m}$ . The IL and extinction rate observed were summarized as in Figures 10 and 11, respectively.

The lowest IL was observed for the 600/800 nm straight/ring waveguide combination with 0.02 dB and was slightly increased to 0.07 dB for the 800/800 nm waveguide combination. The highest extinction rate yields at around 87.3203 % for the dissimilar combination of 800/800 nm waveguide width combination. These results can be predicted since larger waveguide width will cause better optical confinement as explained theoretically in [4]. From both Figures 10 and 11, the waveguide width of 800 nm was suggested for both straight and ring waveguides since low insertion and extinction were obtained.




Figure 9. Power spectrum of different waveguide width designs




Figure 10. Insertion loss of dissimilar combination of straight-ring widths




Figure 11. Extinction Rate of different waveguide width combination

**4. CONCLUSION**

The design of a gallium nitride-based optical microring resonator was studied. It can be concluded that the optimized configuration for the GaN optical microring with PMMA material coating is polymer grafting material PMMA thickness of 0.055  $\mu\text{m}$ , gap separation of 125  $\mu\text{m}$ , straight and ring waveguide length of 800 nm, and ring radius of 10  $\mu\text{m}$ . This study provides a guideline for determining the microring geometry to satisfy the desired filtering requirements.

**ACKNOWLEDGEMENTS**

We would like to thank Universiti Teknikal Malaysia Melaka (UTeM) and the Ministry of Higher Education (MOHE). This research is supported by funding from MOHE via grant no FRGS/1/2020/FKEKK-CETRI/F00425.

## REFERENCES

- [1] X. Li, C. Shen, X. Yu, Y. Zhang, C. Chen, and X. Zhang, "Bandwidth-tunable optical filter based on microring resonator and MZI with Fano resonance," *Journal of Optics*, vol. 49, no. 4, pp. 427–432, 2020, doi: 10.1007/s12596-020-00642-2.
- [2] A. A. Nadia, H. Hazura, and A. R. Hanim, "The potential of silicon photonic devices based on micro-ring resonator," *Journal of Telecommunication, Electronic and Computer Engineering*, vol. 7, no. 1, pp. 17–20, 2015.
- [3] E. Stassen, M. Pu, E. Semenova, E. Zavarin, W. Lundin and K. Yvind, "High Q gallium nitride microring resonators," *2017 Conference on Lasers and Electro-Optics Europe & European Quantum Electronics Conference (CLEO/Europe-EQEC)*, 2017, doi: 10.1109/CLEOE-EQEC.2017.8086619.
- [4] L. Hasanah *et al.*, "Simulation of micro-ring resonator using finite-difference time-domain technique for sensors," *Journal of Engineering Science and Technology*, vol. 15, no. 2, pp. 1267–1276, 2020.
- [5] N. Irawati *et al.*, "Relative Humidity Sensing Using a PMMA Doped Agarose Gel Microfiber," in *Journal of Lightwave Technology*, vol. 35, no. 18, pp. 3940–3944, 15 Sept.15, 2017, doi: 10.1109/JLT.2017.2698044.
- [6] W. Bogaerts *et al.*, "Silicon microring resonators," *Laser Photonics Rev.*, vol. 6, no. 1, pp. 47–73, 2012, doi: 10.1002/lpor.201100017.
- [7] T. H. AlAbdulaal and I. S. Yahia, "Analysis of optical linearity and nonlinearity of Fe<sup>3+</sup>-doped PMMA/FTO polymeric films: New trend for optoelectronic polymeric devices," *Physica B Condensed Matter*, vol. 601, p. 412628, 2021, doi: 10.1016/j.physb.2020.412628.
- [8] I. Krasnokutska, J. L. J. Tambasco, and A. Peruzzo, "Tunable large free spectral range microring resonators in lithium niobate on insulator," *Scientific Report*, vol. 9, no. 1, p. 11086, 2019, doi: 10.1038/s41598-019-47231-3.
- [9] H. Haroon, H. A. Razak, M. Bidin, S. Shaari, and P. Sushita Menon, "Free carrier absorption loss of p-i-n silicon-on-insulator (SOI) phase modulator," *2010 International Conference on Enabling Science and Nanotechnology (ESciNano)*, 2010, pp. 1-2, doi: 10.1109/ESCINANO.2010.5701003.
- [10] Y. Xu, J. Li, and M. Kong, "Various resonance lineshapes available in a single microring resonator," *Journal of Optics*, vol. 23, no. 4, p. 045801, Apr. 2021, doi: 10.1088/2040-8986/abdf33.
- [11] H. LV, Y. Liang, Z. Wu, X. Han, G. Morthier, and M. Zhao, "Polymer-based microring resonator with the multimode interference coupler operating at very-near-infrared wavelengths," *Applied Sciences*, vol. 9, no. 13, p. 2715, 2019, doi: 10.3390/app9132715.
- [12] P. Dong, Y. K. Chen, G. H. Duan, and D. T. Neilson, "Silicon photonic devices and integrated circuits," *Nanophotonics*, vol. 3, no. 4-5, pp. 215–228, 2014, 10.1515/nanoph-2013-0023.
- [13] K. Kumar, M. Bhattacharya, S. Garlapati, and S. Banerjee, "Impact of Gallium Nitride Semiconductor Devices in Tri-state Boost Converter," *2019 IEEE International Conference on Sustainable Energy Technologies and Systems (ICSETS)*, 2019, pp. 292–296, doi: 10.1109/ICSETS.2019.8744791.
- [14] M. H. Chen, W. N. Chou, V. C. Su, C. H. Kuan, and H. Y. Lin, "High-performance gallium nitride dielectric metalenses for imaging in the visible," *Scientific Report*, vol. 11, no. 1, pp. 1-8, 2021, doi: 10.1038/s41598-021-86057-w.
- [15] A. R. Isroi, "Characteristics and Fabrication of Gallium Nitride," in *Conference*, 2015, doi: 10.13140/RG.2.1.2837.9602.
- [16] E. Stassen, M. Pu, E. Semenova, E. Zavarin, W. Lundin, and K. Yvind, "High Q gallium nitride microring resonators," *The European Conference on Lasers and Electro-Optics*, 2017, doi: 10.1109/CLEOE-EQEC.2017.8086619.
- [17] R. W. Purnamaningsih, N. R. Poespawati, and E. Dogheche, "Design of a Four-Branch Optical Power Splitter Based on Gallium-Nitride Using Rectangular Waveguide Coupling for Telecommunication Links," *Journal of Engineering*, vol. 2019, pp. 1-9, 2019, doi: 10.1155/2019/7285305.
- [18] H. Haroon, S. Shaari, P. S. Menon, N. Arsad, and A. R. Hanim, "Design Modeling and Characterizations os SOI-based Parallel Cascaded MRR Array (PCMMRA) By Coupled Mode Theory," *Journal of Telecommunication, Electronic and Computer Engineering*, vol. 7, no. 1, pp. 31–35, 2015.
- [19] Y. C. Lin *et al.*, "Gallium Nitride (GaN) High-Electron-Mobility Transistors with Thick Copper Metallization Featuring a Power Density of 8.2 W/mm for Ka-Band Applications," *Micromachines*, vol. 11, no. 2, p. 222, 2020, doi: 10.3390/mi11020222.
- [20] C. Varnava, "Gate dielectrics improve gallium nitride devices," *Nature Electronics*, vol. 3, no. 1, p. 15, 2020, doi: 10.1038/s41928-020-0371-6.
- [21] H. Haroon, M. Bidin, H. A. Razak, P. S. Menon, N. Arsad and Z. F. M. Napiah, "Impact of coupled resonator geometry on silicon-on insulator wavelength filter characteristics," *2011 IEEE Regional Symposium on Micro and Nano Electronics*, 2011, pp. 380–382, doi: 10.1109/RSM.2011.6088365.
- [22] R. W. Pryor, "Multiphysics modeling using COMSOL®: a first principles approach," *Jones & Bartlett Publishers*, 2009.
- [23] C. BV and C. OY, "COMSOL Multiphysics User's Guide 1998–2010 COMSOL AB.," 1998.
- [24] H. C. Lim, "Optics Modeling and Visualization with Comsol Multiphysics: A Step-By-Step Graphical Modeling and Simulation Guide to Computational Physics with Ray Optics and Wave Optics Modules," *CreateSpace Independent Publishing Platform*, 2018.
- [25] B. Ryu, J. T. Kim, and Y. W. Song, "Graphene-dispersed polymer waveguide for efficient formation of mode-locked lasers at extremely low graphene concentration," *Carbon*, vol. 166, pp. 123–130, 2020, doi: 10.1016/j.carbon.2020.05.016.

- [26] H. Haroon, F. Aliman, S. K. Idris, and H. A. Razak, "Comparative analysis of design parameter variations effect on SOI optical filter performance," *Journal of Physics: Conference Series*, vol. 1151, no. 1, p. 12028, 2019, doi: 10.1016/j.acags.2020.100032.

## BIOGRAPHIES OF AUTHORS



**Hazura Haroon** received B. Eng and M.Eng degrees in Electrical Engineering from Universiti Teknologi Malaysia (UTM), Malaysia in the year 2001 and 2004, respectively. Her doctoral degree is from Universiti Kebangsaan Malaysia (UKM), Malaysia. She has been in teaching profession since 2002. She is currently senior lecturer in Faculty of Electronics and Computer Engineering, Universiti Teknikal Malaysia Melaka (UTeM). Microengineering, Photonics and Optical Communications are the areas of her interest.



**Muhammad Syafiq Ramli** received the bachelor's degree in electronic engineering from Universiti Teknikal Malaysia Melaka (UTeM), Malaysia, in 2020.



**Siti Khadijah Idris**: Othman received her PhD. in Electrical and Electronic Engineering from University of Strathclyde, Glasgow Scotland in 2014 and MSc and BEEE (Hons.) from Universiti Kebangsaan Malaysia in the year 1999 and 2002 respectively. She is currently a Senior Lecturer in Faculty of Electronics and Computer Engineering, Universiti Teknikal Malaysia Melaka (UTeM). Her research interests include OCDMA, Optical Fiber communication and Optical Fiber sensor. She has contributed over 40 technical papers in various journals and conferences.



**Anis Suhaila** received Bachelor Engineering (Electric, Electronics & System) and Master (Microelectronics) degrees from National University of Malaysia (UKM) in 2000 and 2001 respectively. In 2013, she got PhD degree in Electronics and Electrical Engineering from University of Glasgow, U.K. Her research interest includes nanoscale devices, variability and reliability, modelling and simulations, IC design for biomedical applications.



**Hanim Abdul Razak** received Bachelor of Computer and Information Engineering from International Islamic University Malaysia (IIUM) in 2003. Then, she joined KUTKM (now known as UTeM) as a tutor and pursued her MSc in Microelectronics in Universiti Kebangsaan Malaysia (UKM) in which she completed in 2006. After serving UTeM as a lecturer for several years, she was awarded a scholarship to further study in Doctor of Philosophy in Microengineering and Nanoelectronics at Universiti Kebangsaan Malaysia (UKM) and completed in 2014. She is currently a Senior Lecturer in Faculty of Electronics and Computer Engineering, Universiti Teknikal Malaysia Melaka (UTeM). Microengineering, Photonics and Microelectronics are the areas of her interest.



**Thanigai Anbalagan** received the bachelor's degree in electronic engineering from University Technical Malaysia Melaka (UTeM), Malaysia, in 2021. And she is currently working towards the Msc degree at UTeM since april 2021. Her current research focusses in tapered fiber on biomedical applications.